

1 WHAT IS CLAIMED IS:

5

1. A fabrication method of a semiconductor device comprising the steps of:

10 (a) forming a given number of projection electrodes on each of a given number of semiconductor chips, and applying a thermosetting insulating adhesive to areas of mounting parts where the semiconductor chips are to be mounted on a substrate;

15 (b) heating said thermosetting insulating adhesive on said substrate with a half-thermosetting temperature;

20 (c) aligning said semiconductor chips to said mounting parts of the substrate and performing a first fixing of the semiconductor chips with a first pressure; and

25 (d) heating said substrate, on which said semiconductor chips are fixed, with a thermosetting temperature of said thermosetting insulating adhesive, and performing a second fixing of the semiconductor chips with a second pressure.

30

2. The fabrication method of the semiconductor device as claimed in claim 1, wherein the first pressure is lower than the second pressure.

35

3. The fabrication method of the semiconductor device as claimed in claim 1, wherein

Sub
a 4

F

1 said second fixing is simultaneously performed for each
of said semiconductor chips with said second pressure.

5

e

4. The fabrication method of the
semiconductor device as claimed in claim ^{2, 5}, wherein
said ~~second~~ fixing is simultaneously performed for each
10 of said semiconductor chips with said second pressure.

15

Sub
a. 5

5. The fabrication method of the
semiconductor device as claimed in claim 1, wherein
said given number of the projection electrodes are
formed as studs by wire-bonding, the studs being
leveled.

20

H
e

6. The fabrication method of the
semiconductor device as claimed in claim ^{4 or 5} ~~1~~, wherein
said step (a) further comprises the step of (a-1)
forming a conductive adhesive on said projection
electrodes.

30

7. The fabrication method of the
semiconductor device as claimed in claim 5, wherein
35 said step (a) further comprises the step of forming a
conductive adhesive on said projection electrodes.

1

5 8. The fabrication method of the
the step (a-1), said conductive adhesive on the
projection electrodes is formed by a conductive
adhesive, that has been skidded on a plate, and then
transcribed onto the projection electrodes.

10

15 9. A fabrication system of a semiconductor
device comprising:

 a chip loading device forming a given number
of projection electrodes on each of a given number of
semiconductor chips;

20 a substrate loading device loading a
substrate having mounting parts on which said
semiconductor chips are to be mounted;

 an adhesive-application device applying a
thermosetting insulating adhesive to areas of said
mounting parts of the substrate;

25 an alignment-and-pressing device heating said
thermosetting insulating adhesive on said substrate
with a half-thermosetting temperature, aligning said
semiconductor chips to said mounting parts of the
substrate, and performing a first fixing of the
30 semiconductor chips with a first pressure; and

 a pressing-and-heating device heating said
substrate, on which said semiconductor chips are fixed,
with a thermosetting temperature of said thermosetting
insulating adhesive, and performing a second fixing of
35 the semiconductor chips with a second pressure.

1

10. The fabrication system of a semiconductor device as claimed in claim 9, wherein:

5 said alignment-and-pressing device comprises a heat plate for heating said thermosetting insulating adhesive with the half-thermosetting temperature, and bonding heads for aligning said semiconductor chips to said mounting parts and for performing said first
10 fixing with the first pressure; and

 said pressing-and-heating device comprises a stage for heating said substrate with the thermosetting temperature, and pressing-and-heating heads for performing said second fixing with the second pressure
15 with heating the semiconductor chips.

Add E11

20

25

30

35